



Novocanto® Moaré




Novocanto® Moaré




Profile for edges with wavy forms and a large presence, consisting on a base with two insertions made of aluminium. Inspired on baroque forms, Novocanto® Moaré evokes the movement waves of the most delicate fabrics. The new bet of Emac®, converts the edges of ceramic installations into beautiful columns whose soft waves reflect naturally the light. It is delivered in 3 combinations of metallized trendy colors.

General Features



Material:	Anodized aluminium
Lenght:	8ft2in / 2,5 m.l.
Dimensions:	h: 12 mm.
Packaging:	2 u./box With protective film



140 141 139

Applications

Novocanto® Moaré is a profile intended to protect and decorate edges in wall ceramic installations.

Technical Features

Alloy:	6063 (AA and ASTM) L-3441 (UNE 38-301-89)
Fire resistance:	M0 (UNE 23-727-90)
Abrasion resistance:	Very good
Lightfastness:	Excellent
Appearance and color:	EN 12373-1

Materials

Aluminio



Novocanto® Moaré is a profile made by extrusion of aluminium. The bright mirror, matt silver, bright black, matt black, bright gold and matt gold finishes have been anodized, improving mainly through this process their corrosion resistance, mechanical resistance and appearance. The anodized applied has the quality seal Qualanod, which guarantees the quality of the process and the resulting profiles. This seal regulates several tests: appearance and color, thickness measurements, sealing and impregnation control, abrasion resistance, lightfastness, acetic saline chamber and nitric acid immersion.

Aluminium is a material with excellent chemical, physical and mechanical properties. It is lightweight, tough, ductile, malleable and highly durable.

Placement



To see the video, capture this image with your mobile phone (QR code reader software is necessary) or click on it.

1. First, place tiles in one of the walls. Then, spread a big amount of thin-set mortar on the other wall.
2. Place the Novocanto® Moaré on the corner and introduce the side without anchoring wing into the tiled area. Press the profile to make that the thin-set mortar pass through the mechanized anchoring wing.
3. Place tiles along the anchoring wing and press to achieve a perfect adhesion.
4. Continue tiling until the installation is finished.
5. Clean the remaining material and let dry.
6. Finally, remove the protective film if necessary.



Cleaning and maintenance

The cleaning must be done periodically with a soft cloth. If you use a neutral liquid cleaner, you must rinse the profile with cold water and dry to remove excess of moisture. If dirtiness persists, clean the profile with a solution with clean water and detergent or neutral soap 5%, brushing with a cloth that has no particles that could scratch the finish. Ensure the lacquered surface is totally cold (maximum 20°C) before the cleaning.

Steel wool, abrasive cleaners, souring products as well as strong acids (hydrochloric and perchloric), strong bases (caustic soda or ammonia) or carbonated solutions are not recommended. Citric acid is neither recommended because it dissolves the protective layer of the surface of aluminium. Waxes, petrolatum, lanolin or similar substances are not appropriate. Solvents containing haloalkanes (hydrofluoroether and chlorinated solvents) and curing accelerators containing chlorides should not be used (use special accelerators free of chlorides).

Technical Information

You can find out more information about the technical features of Emac®'s products by downloading their Technical File from www.emac.es.

If you have any query please contact our Technical Department in tecnico@emac.es

